

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1. (Currently Amended) An electromagnetic coupling with a pilot clutch for activating a main clutch wherein clutch plates are thrust with a retaining ring moved by magnetic force produced by an electromagnetic coil in the pilot clutch, wherein:

the electromagnetic coil in the pilot clutch is surrounded with stationary ferromagnetic material over at least its rear and outer peripheral ~~two of its three facial~~ sides of its sides other than its magnetic force exerting ~~facial~~ side which is its front side, ~~namely over at least its rear and outer facial sides~~ and further that the ferromagnetic ~~magnetic~~ material is covered with stationary nonmagnetic material.

Claim 2. (Previously Presented) An electromagnetic coupling as set forth in claim 1, wherein at least one of said retaining ring and said clutch plate in the pilot clutch is made of ferromagnetic material.

Claim 3 (Canceled) .

Claim 4. (Currently Amended) An electromagnetic coupling as set forth in claim ~~[[3]]~~ 7, wherein said ferromagnetic material is said spherical graphite cast iron and said spherical graphite cast iron has 0.1 to 1.5 % by weight of Mo added thereto.

Claim 5. (Canceled)

Claim 6. (Currently Amended) An electromagnetic coupling as set forth in claim ~~[[5]]~~ 8, wherein said ferromagnetic material is said spherical graphite cast iron and said spherical graphite cast iron has 0.1 to 1.5 % by weight of Mo added thereto.

Claim 7. (New) An electromagnetic coupling as set forth in claim 1, wherein the ferromagnetic material is one of materials selected from the class which consists of a spherical graphite cast iron having a chemical composition containing by weight 2.7

to 3.9 % of C, 3.3 to 4.8 % of Si, 0.3 to 1.2 % of Mn, $P \leq 0.1$ %, $S \leq 0.1$ %, 0.01 to 0.1 % of Mg, 0.01 to 0.1 % of at least one of Ce and La and the balance Fe and having a carbon equivalent (C-E) ≥ 4.3 and a silicon steel containing by weight 2.8 to 3.3 % of Si, not greater than 1.0 % of Al, 0.1 to 0.2 % of Mn, not greater than 0.002 % of C and the balance Fe.

Claim 8. (New) An electromagnetic coupling as set forth in claim 2, wherein the ferromagnetic material is one of materials selected from the class which consists of a spherical graphite cast iron having a chemical composition containing by weight 2.7 to 3.9 % of C, 3.3 to 4.8 % of Si, 0.3 to 1.2 % of Mn, $P \leq 0.1$ %, $S \leq 0.1$ %, 0.01 to 0.1 % of Mg, 0.01 to 0.1 % of at least one of Ce and La and the balance Fe and having a carbon equivalent (C-E) ≥ 4.3 and a silicon steel containing by weight 2.8 to 3.3 % of Si, not greater than 1.0 % of Al, 0.1 to 0.2 % of Mn, not greater than 0.002 % of C and the balance Fe.